

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



INTERNATIONAL BUREAU OF PATENT COOPERATION
358, RUE DE LA PATENTE
CH-1202 GENEVE 20
SUISSE

(43) International Publication Date
19 April 2001 (19.04.2001)

PCT

(10) International Publication Number
WO 01/27382 A1

- (51) International Patent Classification⁷: D06N 7/00, (US). HUFFINES, Prentice, Lee; 114 Fields Drive, Old Hickory, TN 37138 (US).
A47G 27/04, B32B 27/12
- (21) International Application Number: PCT/US00/28150 (74) Agent: MAYER, Nancy, S.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).
- (22) International Filing Date: 12 October 2000 (12.10.2000)
- (25) Filing Language: English (81) Designated States (*national*): AU, CA, JP.
- (26) Publication Language: English (84) Designated States (*regional*): European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).
- (30) Priority Data:
60/158,786 12 October 1999 (12.10.1999) US
09/669,477 25 September 2000 (25.09.2000) US
- (71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US).
- (72) Inventors: MURPHY, Peter, Michael; 5024 Branstons Road, Ooletwah, TN 37363 (US). SUMMERS, James, Thomas; 1066 Hillview Drive, Henderson, TN 37075
- Published:
— With international search report.
— Before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments.
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



WO 01/27382 A1

(54) Title: LIQUID IMPERMEABLE, MOISTURE VAPOUR PERMEABLE CARPET UNDERLAY

(57) Abstract: A carpet underlay comprising a composite of a fibrous substrate and a film affixed to said substrate which is impermeable to liquids and permeable to moisture vapor is disclosed.

LIQUID IMPERMEABLE, MOISTURE VAPOUR PERMEABLE CARPET UNDERLAY.

5

BACKGROUND OF THE INVENTION

Water resistant carpet underlays provide a way to clean spills on carpet more thoroughly by helping to contain the spill above the padding or floor. If a spill is not removed from under the carpet, the spill will allow the growth of mold, mildew, and bacteria. Not only may the padding and wood flooring deteriorate as a result, but such conditions are conducive to the formation of odors and allergens. Spills on fitted or wall-to-wall carpeting are particularly insidious since detection and prevention of the seepage into the padding following a spill is typically impractical with large or fitted carpets. A spill on broadloom carpeting often puddles on the padding or flooring where it can not be removed by cleaning. This spill then accelerates the growth of mold, mildew and odors.

Murphy, in US Patents 5,601,910 and 5,763,040, described processes for chemically treating an underlay with a repellent finish to make it substantially impermeable to spills. By careful selection of both the water repellent finish and adhesive, the underlay was adhered to the underside of the carpet creating a barrier substantially impervious to spills.

The prior art also describes water impermeable carpeting constructed using sheets of plastic, such as polyethylene and poly(ethylene/vinyl acetate), that are laminated to the carpet. However, such backings are expensive, create manufacturing difficulties, and prevent desirable breathability (air permeability) of the carpet. Thus the growth of mold and mildew are not prevented.

Following a spill, the well-intentioned but perhaps distraught homeowner will frequently lay paper towels or other absorbent material on the spill and stamp or otherwise apply an excessive downward force on the spill area, rather than just gently absorbing the spill. Stamping on the spill or on absorbent material laid over the spill can force liquid through water repellent underlays of the prior art. While the nonbreathable thermoplastic films such as poly(ethylene) are sufficiently impermeable to resist the application of the homeowner's weight, such

underlays as a fluorocarbon-treated non-woven fabric will allow moisture to pass through when excessive weight is applied.

5 It would be advantageous if an improved underlay material could be fabricated that would maintain its water impermeability even when spills are absorbed by stamping on an absorbent material laid over the spill. It is also desirable that the underlay is air permeable so that moisture is not trapped beneath it leading to mold and mildew. The present invention provides such an improved underlay having liquid impermeability while maintaining vapor breathability.

10

SUMMARY OF THE INVENTION

15 The present invention comprises a carpet underlay comprising a composite of a fibrous substrate having opposite first and second planar sides, and at least one film affixed to the first side of said substrate, said underlay impermeable to liquids and permeable to moisture vapor.

20 The present invention further comprises a carpet underlay comprising a composite of a fibrous substrate, an optional control layer affixed to said substrate, a tie layer affixed to said control layer or to said substrate, and a moisture vapor permeable film affixed to said tie layer, said underlay impermeable to liquids and differentially permeable to moisture vapor.

25 The present invention further comprises a tufted pile carpet comprising: a) a primary backing having a surface tufted with pile yarns and an underside to which a latex has been applied; b) an optional secondary backing having a surface and an underside, wherein the surface of the secondary backing is adhered to the underside of the primary backing; and c) an underlay of the present invention as described above adjacent to or affixed to the primary or secondary backing.

30

The present invention further comprises a carpet cushion of a material providing resiliency, support, or noise reduction having opposite first and second planar sides and having adjacent to or affixed to one of said sides an underlay of the present invention as described above.

The present invention further comprises a process for rendering a carpet or a carpet cushion impermeable to liquids and permeable to moisture vapor comprising placing adjacent to or affixing to an underside of said carpet or said carpet cushion an underlay of the present invention as described above.

DETAILED DESCRIPTION OF THE INVENTION

The present invention comprises a carpet underlay comprising a composite of a fibrous substrate having opposite first and second planar sides, and at least one film affixed to the first side of said substrate, said underlay exhibiting impermeability to liquids and permeability to moisture vapor. The film is formed from a polymeric material that is impermeable to liquids but through which water vapor can readily permeate. Important attributes of the underlay or impermeable barrier for carpets provided by the present invention are (1) the ability to keep the underlying carpet pad and floor dry under a wide range of spills and cleaning techniques, and (2) the ability to prevent the retention of trapped moisture under the barrier by allowing it to evaporate promptly.

The term "breathable liquid-impermeable underlay" is used hereinafter to describe such composites comprising a fibrous substrate affixed to a film formed from a polymeric material that is impermeable to liquids but through which moisture vapor can readily permeate.

The term "breathable" denotes a moisture vapor transport rate of 100 g/m²/day or more, determined by Test Method 2 described below.

The terms "permeable", "vapor breathability", and "air permeability" are used interchangeably with "breathable" herein.

The term "impermeable" signifies a "dry" rating under the conditions of Test Method 1 described below.

The term "carpet cushion" as defined by The Carpet and Rug Institute (CRI), located in Dalton GA, means any kind of material placed under carpet to provide resiliency, support, and noise reduction when walked upon (CRI 105 "Residential Carpet Installation Standards").

5

The term "padding" or "pad" is considered synonymous with "carpet cushion".

Trademarks and tradenames are indicated by capitalization herein.

10

The invention provides a moisture vapor permeable, liquid impermeable composite comprising a fibrous substrate and at least one film. The composite is a laminate or a coating product and is free of pinholes or pores. As used herein, pinholes means small holes inadvertently formed in the film, while pores means
15 small holes formed intentionally to enhance porosity to air, moisture, vapor, or liquids.

The fibrous substrate component of the breathable liquid-impermeable underlay is any woven or non-woven fabric or web, and is preferably a light non-
20 woven fabric, selected from the group consisting of polyester, polyolefin, polyamide, poly(trimethylene terephthalate) synthetic fibers, natural fibers, bicomponent fibers, cellulosic fibers, wool, cotton, acrylic, jute, and copolymers and blends thereof. By the term "cellulosic" is meant fibrous cellulose-based products made from wood or other plants. Bicomponent fibers include fibers
25 made of two polymers, blends of polymeric fibers with natural or synthetic fibers, and blends of natural and synthetic fibers. Suitable nonwoven materials include spunbonded webs, scrims, carded webs, flashspun webs, or nonwoven sheets comprised of blends of polymer fibers. Preferred are underlays wherein the fibrous substrate is a polyester spun-laced nonwoven fabric.

30

Particularly preferred are nonwoven fabrics such as SONTARA, a spun-laced nonwoven fabric available from E. I. du Pont de Nemours and Company, Wilmington DE. SONTARA is a spunlaced fabric formed by a hydroentangling process in which staple fibers are entangled through "hydraulic needling" to form

a strong, fabric-like structure. SONTARA consists of fibers and/or wood pulp entangled in predetermined, repeating patterns forming strong structures without binder and having tensile strength greater than one pound per inch of fabric width for each ounce per square yard (5.3 g per cm fabric width for each g/m²). The
5 manufacture of SONTARA is described in US Patents 3,797,074 and 3,485,706.

The film component of the breathable liquid-impermeable underlay is any solid and void- and pore-free polymeric film through which water molecules may readily diffuse. The film is impermeable to liquids, and permeable to moisture
10 vapor. It is typically a thermoplastic or thermoset polymer material that can be coated or extruded or laminated. Suitable polymers include vulcanized silicone rubbers, silicone polymers, polyurethanes, polyether esters, polyether amides, polyurethane esters, polyurethane ethers, polyvinyl alcohol, and copolymers and blends thereof. Particularly preferred are films of HYTREL, a
15 butylene/poly(alkylene ether) phthalate copolymer available from E. I. du Pont de Nemours and Company, Wilmington DE.

Also suitable for use in this invention are film components wherein either (a) the film has a first layer and second layer, each of said layers being comprised
20 of a different moisture vapor permeable polymer composition, or (b) the film has one hydrophilic layer and one hydrophobic layer. Such films having a bicomponent structure are described in US Patent 4,725,481. Use of a bicomponent film of a hydrophilic layer and a hydrophobic layer bonded together permits differential transfer of moisture vapor to prevent buildup of moisture.
25 This is because the bicomponent film has a separation ratio for water vapor of at least about 1.2 as determined by ASTM E-96-66 (Procedure BW). The separation ratio for water vapor is described by the ASTM method as the value of the water vapor transmission rate measured with the hydrophilic layer of the film next to the water surface divided by the value of the water vapor transmission rate of the film
30 with the hydrophobic layer next to the water surface. Generally the film has a higher water vapor transmission rate when water vapor passes in the direction of the hydrophilic layer of film and then through the hydrophobic layer. Thus in the underlay of the present invention, placement of the hydrophilic layer of film next to the floor or the padding results in a reduction of accumulation of moisture

vapor between the underlay and the floor or padding due to the higher rate of transmission from the hydrophilic layer through the hydrophobic layer. The water vapor transmission rates of the hydrophilic and hydrophobic layers can be regulated by the thickness of the layer and the chemical composition of the layer.

5

A second embodiment of the present invention comprises a breathable liquid-impermeable underlay comprising a composite of a fibrous substrate, an optional control layer affixed to said substrate, a tie layer affixed to said control layer or to said substrate, and a moisture vapor permeable film affixed to said tie layer, said underlay exhibiting impermeability to liquids and differential permeability to moisture vapor. In this embodiment an optional control layer is positioned between the fibrous substrate and a tie layer. This control layer acts as a vapor control layer. Preferably, the optional control layer is a polymer capable of reducing the moisture vapor transmission rate of the composite. The control layer is selected from the group consisting of polyethylene, polypropylene or a copolymer thereof. In this embodiment, a tie layer is present between the fibrous substrate or optional control layer and the moisture vapor impermeable film. The tie layer functions to improve adhesion to the fibrous substrate. The tie layer is capable of compatibilizing the fibrous substrate or control layer and the film layer and forms a strong bond with both. It also works in combination with the moisture vapor impermeable film to enable the composite to exhibit differential permeability. The tie layer can also comprise further additives known in the art. Preferably the tie layer is a copolymer of ethylene co-monomer units and vinyl acetate co-monomer units. Structure of such control layer, tie layer, and moisture vapor permeable layer are described in patent application, US Serial number 60/158,786 (docket number AD-6649-P1).

The composite of the second embodiment is capable of exhibiting differential permeability. The moisture vapor transmission rate in one direction through the layers of the composite is greater than that in the opposite direction. The moisture vapor transmission rate in the direction away from the film layer and tie layer and towards the fibrous substrate layer is greater than the moisture vapor transmission rate in the direction away from the substrate layer and towards the tie layer and film layer. The moisture vapor transmission rate of each layer is

primarily dependent upon the chemical composition of the layer and the thickness of the layer. These parameters can be adjusted to optimize performance.

5 The composites of the present invention are prepared by lamination or coating techniques. The film is laminated to or coated on the fibrous substrate by any of various methods well known to those skilled in the art in an amount sufficient to provide liquid impermeability and a moisture vapor transport rate (MVTR) of at least 100 g/m²/day. Such methods include the use of adhesives (adhesive lamination), heat bonds (thermal lamination), pressure bonding,
10 ultrasonic bonding, dynamic mechanical bonding, and extrusion coating, or any other suitable attachment means, or combinations of these attachment means.

Processes for the extrusion melt coating of a polymer resin onto non-woven or other substrates are well known. The process generally involves the
15 steps of heating the polymer to a temperature above its melting point, extruding it through a flat die onto a substrate which passes through the curtain of molten polymer, subjecting the coated substrate to pressure to effect adhesion, and then cooling. The extrusion melt coating method is widely used since it allows economical production of a laminated structure in a one-step procedure.

20

Conveniently, formation of the laminate structure of the invention, optionally including the control layer, is effected by coextrusion of the respective layers onto the substrate, either by simultaneous coextrusion of the respective layers through independent orifices of a multi-orifice die, and thereafter uniting
25 the still molten layers, or, preferably, by single-channel coextrusion in which molten streams of the respective polymers are first united within a channel leading to a die manifold, and thereafter extruded together from the die orifice under conditions of streamline flow without intermixing onto the substrate.

30 Conventional laminating techniques may also be used, for example by lamination of a preformed film layer and a preformed tie layer, or a preformed film layer, a preformed tie layer and a preformed control layer, either before or simultaneously with lamination thereof with the substrate, or by casting. Typically, such lamination techniques would involve thermal lamination of the

respective layers on hot roll calendering equipment, wherein the temperature used to bond the layers to the substrate is sufficient to effect melting or softening of one or more layers, and with the application of sufficient pressure, the layers become bonded.

5

Preferably, the process is an extrusion coating process wherein the tie layer is coextruded with said film layer, or, if the control layer is included, wherein the control layer, the tie layer, and the film layer are coextruded together. Minimum film thickness can be less than 1 mil (25 μ m). The moisture vapor permeable film is substantially free of pinholes or pores. Extrusion coating a thin layer of the film onto the fibrous substrate is a preferred manufacturing technique.

10

The breathable liquid-impermeable underlays of this invention are used alone, underneath but not attached to an overlying carpet, underneath and attached to an overlying carpet, underneath an overlying carpet and attached to padding, or any combination thereof.

15

The breathable liquid-impermeable underlays of the present invention show improved liquid impermeability, especially impermeability to liquids under pressure, such liquids as water, hot and cold beverages, oils, detergent solutions, and alcohols. For example, a film of HYTREL laminated to a SONTARA non-woven fabric provides better liquid impermeability than SONTARA treated with a water repellant while maintaining a high moisture vapor transport rate. The fibrous substrate provides the strength and dimensional stability at a lower cost than an equal strength film of the HYTREL alone, which provides the liquid impermeability. The breathable liquid-impermeable underlay is laid with the film layer on top or underneath, and preferably with the film on top. The breathable liquid-impermeable underlay is laid under the carpet either unattached to the carpet, or affixed to the carpet or affixed to the padding by any conventional method that does not involve puncturing the underlay.

20

25

30

The present invention further comprises a tufted pile carpet comprising:

- a) a primary backing having a surface tufted with pile yarn and an underside to which a latex has been applied;
- b) an optional secondary backing having a surface and an underside,
5 wherein the surface of the secondary backing is adhered to the underside of the primary backing; and
- c) an underlay of the present invention as previously described.

An underlay of the present invention described above is laid below, or
10 optionally affixed to, the underside of the carpet by an adhesive applied to the upper side of the underlay. Alternatively the underlay is treated with adhesive on both sides to attach it to both the underside of the carpet and the padding. Such attachment prevents movement of the underlay as the carpet is laid, and also prevents any movement due to traffic after the installation is complete, but liquid
15 impermeability of the barrier does not require attachment.

The present invention further comprises a carpet cushion of a material providing resiliency, support, or noise reduction having opposite first and second planar sides and having adjacent to or affixed to one side an underlay of the
20 present invention as described above. The optional attachment of the underlay to either surface of the cushion using conventional adhesion techniques.

The present invention further comprises a process for rendering carpet or carpet cushion impermeable to liquids and permeable to moisture vapor
25 comprising placing adjacent to or affixing to a surface of said carpet or cushion an underlay of the present invention as described above.

The underlay of the present invention is useful to provide an impermeable barrier between a carpet and carpet cushion, between a carpet and floor, or
30 between a carpet cushion and floor. Thus the floor and carpet cushion remain dry under a wide variety of spills and cleaning techniques. The underlay also prevents retention of any trapped moisture by allowing evaporation. This prevents damage to the carpet cushion and floor and prevents the formation of mold and mildew.

TEST METHODS

Test Method 1. Water Impermeability

5

A 5-layer test stack was prepared as follows: (1) A sample of residential carpeting with water permeable, latex was placed over (2) the underlay sample which was in turn placed on (3) a white absorbent paper towel placed over (4) rebond carpet padding which was placed over (5) a wood particle board sheet.

10

The paper towels used were single-fold paper towels available from Kimberly-Clark, Dallas TX. Since the test requires no visible wetness of the towel, the choice of paper towel is not critical and other thin absorbent media, such as Whatman No.1 Filter paper may be substituted. A colored aqueous solution may be used to aid visual detection. Then 100 ml of water, at a room temperature of 24 +/- 3°C (75+/- 5°F) was slowly poured onto the carpet sample through a cylinder of about 8 cm diameter and from a height of about 1 meter to create a circular puddle. The cylinder was removed and the sample was left undisturbed for 20 minutes. For the 0 psi (0 kPa, i.e. spill only test) the carpet and underlay were removed. If any water spot was visible on the towel (designated "wet" in the results), then the underlay was judged a failure to provide sufficient water impermeability to a water spill. If the paper towel between the padding and carpet was dry (designated "dry" in the results), the underlay was judged acceptable and provided sufficient water impermeability to a water spill.

Alternatively, the water was "blotted" from the carpet pile with dry paper towels at a given pressure. After ten "blottings" with the given pressure, the carpet and underlay were removed. If any water spot was visible on the towel, then the underlay was judged a failure (or "wet") and did not provide sufficient water impermeability for a water spill followed by blotting at the given pressure. If the paper towel between the padding and carpet was "dry", the underlay was judged to provide sufficient water impermeability for a water spill followed by blotting at the given pressure. Blotting pressures of 0, 3, 8, 16, and 33 psi (0, 21, 55, 110, and 227 kPa) were utilized. A blotting pressure of 33 psi or 228 kPa exceeds the pressure exerted by a typical homeowner standing on a paper towel to accelerate the blotting of a spill. After a "wet" or fail rating, tests at higher blotting pressures

35

were not made (denoted by "X" in Table 1). The blotting pressures were created by placing weights on a circular disc as follows:

| Total weight of plate and weights[lb (kg)] | Plate diam. [in ² (cm ²)] | Resulting pressure [psi (kPa)] |
|--|--|--------------------------------|
| 42 (19) | 14 (90) | 3 (21) |
| 110 (50) | 14 (90) | 8 (55) |
| 220 (100) | 14 (90) | 16 (110) |
| 220 (100) | 6.7 (43) | 33 (228) |

5

Test Method 2. Moisture Vapor Transport Rate.

The Moisture Vapor Transport Rate (MVTR) is measured in an "up cup" configuration, over a saturated head of water vapor according to the procedure described the American Society for Testing Materials (ASTM) Standard ASTM

10 E96-92.

EXAMPLES

In the following examples, all carpet samples were purchased commercially from Carpets of Dalton, Dalton, GA. Sources of other materials are listed after Table 1.

Examples 1, 2, 3

HYTREL 4778 was fed to a 1.5-inch (3.8 cm) diameter extruder connected to a melt combining block, heated to about 225°C, and extruded at 25 rpm. The molten HYTREL 4778 then passed through a die connected to the combining block having a 35 inch (89 cm) wide die block heated to about 225°C. A film was formed exiting from the die that had a thickness of 1 mil (25µm). The film exiting from the die was coated on a nonwoven lightweight scrim fabric of spun bonded polyethylene terephthalate (SONTARA 8000) as a substrate. The underlay was tested according to Test Methods 1 and 2 using the following carpets: 1) 28 oz/yd² (950g/m²) Berber level loop polypropylene carpet, 2) 42 oz/yd² (1425 g/m²) nylon cut-pile carpet, and 3) 65 oz/yd² (2200g/m²) nylon cut-pile carpet. The results are shown in Table 1 as Examples 1, 2 and 3 respectively.

Examples 4, 5, 6

HYTREL 8206 was fed to a 1.5 inch (3.8 cm) diameter extruder connected
5 to a melt combining block. HYTREL 4778 was fed to a 1 inch (2.5 cm) diameter
extruder that was also connected to the same melt combining block. The
HYTREL 8206 was heated to about 225°C and coextruded at 20 rpm and the
HYTREL 4778 was heated to about 225°C and coextruded at 10 rpm to the melt
combining block connected to the extruders. The coextruded layers were
10 combined in the melt block. The layers were then passed through a die connected
to the combining block having a 35 inch (89 cm) wide die block heated to about
225°C. A bonded bicomponent film was formed exiting from the die that had a
combined thickness of 1 mil (25µm). The HYTREL 8206 was 0.8 mil (20µm)
thick, and the HYTREL 4778 was 0.2 mil (5µm) thick. The bicomponent film
15 exiting from the die was coated on a nonwoven lightweight scrim fabric of spun
bonded polyethylene terephthalate (SONTARA 8000) as a substrate with the
HYTREL 8206 layer next to the scrim fabric. The underlay was tested according
to Test Methods 1 and 2 using the following carpets: 1) 28 oz/yd² (950g/m²)
Berber level loop polypropylene carpet, 2) 42 oz/yd² (1425 g/m²) nylon cut-pile
20 carpet, and 3) 65 oz/yd² (2200g/m²) nylon cut-pile carpet. The results are shown
in Table 1 as Examples 4, 5 and 6 respectively.

Examples 7, 8, 9

These extrusion coated fabrics were made according to the procedure in
25 Example 4, with the exception that the polymer extruder rpm and die thickness
resulted in a film thickness of 0.6 mil (15µm). The underlay was tested according
to Test Methods 1 and 2 using the following carpets: 1) 28 oz/yd² (950g/m²)
Berber level loop polypropylene carpet, 2) 42 oz/yd² (1425 g/m²) nylon cut-pile
carpet, and 3) 65 oz/yd² (2200g/m²) nylon cut-pile carpet. The results are shown
30 in Table 1 as Examples 7, 8 and 9 respectively.

Examples 10, 11, 12

These extrusion coated fabrics were made according to the procedure in
Example 1 except that the fabric substrate was SONTARA 8004. The underlay
35 was tested according to Test Methods 1 and 2 using the following carpets: 1) 28

oz/yd² (950g/m²) Berber level loop polypropylene carpet, 2) 42 oz/yd² (1425 g/m²) nylon cut-pile carpet, and 3) 65 oz/yd² (2200g/m²) nylon cut-pile carpet. The results are shown in Table 1 as Examples 10, 11 and 12 respectively.

5 Examples 13, 14 and 15.

These extrusion coated fabrics were made according to the procedure in Example 1 except that HYTREL blend P18-3892 was substituted for HYTREL 4778 and the fabric substrate was HDK powder bonded nonwoven. The underlay was tested according to Test Methods 1 and 2 using the following carpets: 1) 28
10 oz/yd² (950g/m²) Berber level loop polypropylene carpet, 2) 42 oz/yd² (1425 g/m²) nylon cut-pile carpet, and 3) 65 oz/yd² (2200g/m²) nylon cut-pile carpet. The results are shown in Table 1 as Examples 13, 14 and 15 respectively.

Example 16

15 KC MICROCOOL laminate nonwoven fabric (described in the footnotes to Table 1 below) was used as purchased as the underlay and tested according to Test Methods 1 and 2 using a 28 oz/yd² (950 g/m²) Berber level loop polypropylene carpet. The results are shown in Table 1.

20 Examples 17 and 18

HYTREL G4778, a polyether-ester block copolymer, was dried and fed into an extrusion hopper. A 1.5-inch (3.8 cm) diameter extruder connected to a 14-inch (35.6 cm) coat hanger die block was heated up to 220°C. The molten polymer was extruded at 20 rpm. The film formed from the die was deposited
25 onto a 0.9 oz/yd² (31 g/m²) spunbonded polyester (SBPET) nonwoven fabric between nip and casting rolls. The nip and casting roll temperatures were 28°C. The nip roll pressure was 80 psi (550 kPa). The film thickness was controlled by the coating line speed. The Example 17 sample having a 0.8 mil (20 µm) film thickness was produced by a line speed of 60 feet per minute (18.3 meters per
30 minute). The line speed for the Example 18 sample was 42 feet per minute (12.8 meters per minute) which produced a 1.0 mil (25 µm) film thickness. The underlays were tested according to Test Methods 1 and 2 using a 28 oz/yd² (950 g/m²) Berber level loop polypropylene carpet. The results are shown in Table 1.

Examples 19 and 20

HYTREL G4778 (a polyether-ester block copolymer) was dried and fed into an extrusion hopper. A 1.5-inch (3.8 cm) diameter extruder connected to a
5 14-inch (35.6 cm) coat hanger die block was heated up to 220°C. The molten polymer was extruded at 20 rpm. The film formed from the die was deposited onto a 0.5 oz/yd² (17 g/m²) spunbonded polyester (SBPP) nonwoven fabric between nip and casting rolls. The nip and casting roll temperatures were 28°C. The nip roll pressure was 80 psi (550 kPa). The film thickness was controlled by
10 the coating line speed. The line speed for the Example 19 sample was 42 feet per minute (12.8 meters per minute) which produced a 1.0 mil (25 µm) film thickness. The Example 20 sample having a 0.8 mil (20 µm) film thickness was produced by a line speed of 60 feet per minute (18.3 meters per minute). The underlays were tested according to Test Methods 1 and 2 using a 28 oz/yd² (950 g/m²) Berber
15 level loop polypropylene carpet. The results are shown in Table 1.

Examples 21 and 22

HYTREL G4778 (a polyether-ester block copolymer) and BYNEL 50E631 (an anhydride-modified polypropylene resin) were dried and fed into an
20 extrusion hopper at a weight ratio of 87% HYTREL and 13% BYNEL. A 1.5-inch (3.8 cm) diameter extruder connected to a 14-inch (35.6 cm) coat hanger die block was heated up to 220°C. The molten polymer was extruded at 20 rpm. The film formed from the die was deposited onto a 0.5 oz/yd² (17 g/m²) spunbonded polypropylene (SBPP) nonwoven fabric between nip and casting rolls. For
25 Example 21 and 22 samples, the nip roll temperature was 80°C and the casting roll temperature was 40°C. The nip roll pressure was 80 psi (550 kPa). The film thickness was controlled by the coating line speed. The line speed for the Example 22 sample was 42 feet per minute (12.8 meters per minute) which produced a 1.0 mil (25 µm) film thickness. The Example 21 sample having a 0.8
30 mil (20 µm) film thickness was produced by a line speed of 60 feet per minute (18.3 meters per minute). The underlays were tested according to Test Methods 1 and 2 using a 28 oz/yd² (950 g/m²) Berber level loop polypropylene carpet. The results are shown in Table 1.

Table 1. Impermeability Tests Results for Various Underlay Treatments.

| | | | Paper Towel Appearance After 10 Blottings under Pressure (b) | | | | |
|---|---|---------------------------------|--|-----------------|-------------------|-------------------|----------------------------------|
| Ex | Underlay Fabric/Underlay Film (a) | Spill Only 0 psi 0 kPa | 3 psi 21 kPa | 8 psi 55 kPa | 16 psi 110 kPa | 33 psi 228 kPa | MVTR(c) g/m ² /day |
| (i) 28 oz/yds (950 g/m ²) Berber, Level Loop Polypropylene Carpet | | | | | | | |
| Comparative Examples: | | | | | | | |
| A | SONTARA 8827 treated with 3% fabric protector (d)/none | dry | dry | wet | X | X | 1100 |
| B | SONTARA 8827 treated with 4% fabric protector (d)/none | dry | dry | dry | wet | X | 800 |
| C | 4 mil (25µm) polyethylene film/none | dry | dry | dry | dry | dry | 0 |
| D | W/H Housewrap/none | wet | X | X | X | X | 200 |
| E | O-C Housewrap/none | wet | X | X | X | X | 100 |
| F | TYVEK HomeWrap/none | dry | wet | X | X | X | 400 |
| Examples: | | | | | | | |
| 1 | SONTARA 8000/1 mil (25µm) HYTREL 4778 | dry | dry | dry | dry | dry | 600 |
| 4 | SONTARA 8000/1 mil (25µm) HYTREL CO-EX | dry | dry | dry | dry | dry | 700 |
| 7 | SONTARA 8000/0.6 mil (15µm) HYTREL CO-EX | dry | dry | dry | dry | dry | 800 |
| 10 | SONTARA 8004/1 mil (25µm) HYTREL 4778 | dry | dry | dry | dry | dry | 600 |
| 13 | HDK/0.7 mil (18µm) HYTREL blend | dry | dry | dry | dry | dry | 600 |
| 16 | KC MICROCOOL | dry | dry | dry | dry | dry | 350 |
| 17 | SBPET/0.8 mil (20 µm) HYTREL G4778 | dry | dry | dry | dry | dry | 170 |
| 18 | SBPET/1.0 mil (25 µm) HYTREL G4778 | dry | dry | dry | dry | dry | 160 |
| 19 | SBPP/1.0 mil (25 µm) HYTREL G4778 | dry | dry | dry | dry | dry | 190 |
| 20 | SBPP/0.8 mil (20 µm) HYTREL G4778 | dry | dry | dry | dry | dry | 160 |
| 21 | SBPP/0.8 mil (20 µm) HYTREL G4778 (87%) & BYNEL 50E631 (13%) by Weight | dry | dry | dry | dry | dry | 190 |
| 22 | SBPP/1.0 mil (25 µm) HYTREL G4778 (87%) & BYNEL 50E631 (13%) by Weight | dry | dry | dry | dry | dry | 200 |
| (ii) 42 oz/yd ² (1425 g/m ²) Nylon Cut-Pile Carpet | | | | | | | |

Table 1 (Cont'd.)

| Comparative Examples: | | | | | | | |
|--|--|-----|-----|-----|-----|-----|------|
| G | SONTARA 8827 treated with a 3% fabric protector (d)/none | dry | dry | wet | X | X | 1100 |
| Examples: | | | | | | | |
| 2 | SONTARA 8000/1 mil (25 μ m) HYTREL 4778 | dry | dry | dry | dry | dry | 600 |
| 5 | SONTARA 8000/1 mil (25 μ m) HYTREL CO-EX | dry | dry | dry | dry | dry | 700 |
| 8 | SONTARA 8000/0.6 mil (15 μ m) HYTREL CO-EX | dry | dry | dry | dry | dry | 800 |
| 11 | SONTARA 8004/1 mil (25 μ m) HYTREL 4778 | dry | dry | dry | dry | dry | 600 |
| 14 | HDK/0.7 mil (18 μ m) HYTREL blend | dry | dry | dry | dry | dry | 600 |
| (iii) 65 oz/yd ² (2200 g/m ²) Nylon Cut-Pile Carpet | | | | | | | |
| Comparative Examples: | | | | | | | |
| H | SONTARA 8827 treated with 3% fabric protector (d)/none | dry | dry | wet | X | X | 1100 |
| Examples: | | | | | | | |
| 3 | SONTARA 8000/1 mil (25 μ m) HYTREL 4778 | dry | dry | dry | dry | dry | 600 |
| 6 | SONTARA 8000/1 mil (25 μ m) HYTREL CO-EX | dry | dry | dry | dry | dry | 700 |
| 9 | SONTARA 8000/0.6 m (15 μ m) HYTREL CO-EX | dry | dry | dry | dry | dry | 800 |
| 12 | SONTARA 8004/1 mil (25 μ m) HYTREL 4778 | dry | dry | dry | dry | dry | 600 |
| 15 | HDK/0.7 mil (18 μ m) HYTREL blend | dry | dry | dry | dry | dry | 600 |

- 5 (a) SONTARA 8000 and 8004 are 1.2 and 1.6 oz/yd² (41 and 54 g/m²), respectively, spunlaced nonwoven polyester fabric available from E. I. du Pont de Nemours and Company, Wilmington DE.

- 10 SONTARA 8827 is a 2 oz/yd² (68 g/m²) spunlaced nonwoven fabric having a composition of 55%/45% weight percent wood pulp/polyester available from E. I. du Pont de Nemours and Company, Wilmington DE.

- 15 HDK is a 1 oz/yd² (34 g/m²) polyester, powder bonded, non-woven fabric available from H.D.K. Industries Inc., Greenville SC.

HYTREL 4778 is a copolyether ester thermoplastic elastomer,
having a melting point of 208°C, a vicat softening temperature of
5 175°C, a shore hardness of 47D, and a water absorption of 2.3%.
HYTREL 4778 available from
E. I. du Pont de Nemours and Company, Wilmington DE.

HYTREL 8206 is a copolyether ester thermoplastic elastomer,
10 having a melting point of 200°C, a vicat softening temperature of
151°C, a shore hardness of 45D, and a water absorption of 30%
available from by E. I. du Pont de Nemours and Company,
Wilmington DE.

15 HYTREL Blend is a Du Pont HYTREL film blend No. P18-3892
available from Clopay Corp., Cincinnati OH.

HYTREL CO-EX denotes an extrusion coating of first a layer of
80% by weight of HYTREL 8206 on the fabric followed by a 20%
20 by weight of a second extrusion coating layer of HYTREL 4778.

TYVEK HomeWrap is a 1.8 oz/yd² (61 g/m²) spunbond olefin
nonwoven fabric available from by
E. I. du Pont de Nemours and Company, Wilmington DE.

25 W/H Housewrap is Weyerhaeuser CHOICE WRAP Housewrap
manufactured by Weyerhaeuser, Tacoma WA.

O-C Housewrap is Owens-Corning PINKWRAP Housewrap
30 manufactured by Owens-Corning, Toledo, OH.

The spunbonded polyester (SBPET), a nonwoven fabric with a
basis weight of 0.9 oz/yd² (31 g/m²), is available from American
Non-wovens, Vernon, AL.

35

The spunbonded polypropylene (SBPP), a nonwoven fabric with a basis weight of 0.5 oz/yd² (17 g/m²), is available from ATEX, Gainesville, GA.

5 HYTREL G4778 is a thermoplastic polyester elastomer made of polyether-ester block copolymers manufactured by E. I. du Pont de Nemours and Company, Wilmington, DE.

10 BYNEL 50E631 is an anhydride-modified polypropylene resin manufactured by E. I. du Pont de Nemours and Company, Wilmington, DE.

15 KC MICROCOOL is a laminate nonwoven fabric available from Kimberly-Clark, Irving, TX and believed to be a tri-layer structure with two outside layers of spunbonded polypropylene and a middle layer of microporous polypropylene film made by incorporation of calcium carbonate in the polypropylene film followed by stretching in the machine direction to create the microporous film prior to thermal bonding lamination. Although "microporous", the KC
20 MICROCOOL fabric acts as a breathable liquid-impermeable underlay, passing the requirements of Test Methods 1 and 2, as shown in Table 1 for Example 16.

(b) By Test Method 1.

25

(c) Moisture vapor transmission rate, by Test Method 2.

(d) The SONTARA 8827 was pretreated with the indicated amount of a fabric protector emulsion described in US Patent 5,344,903. The
30 emulsion contained a copolymer of acrylic and methacrylic fluorochemical esters manufactured by E. I. du Pont de Nemours and Company, Wilmington DE.

The results in Table 1 showed the Example breathable liquid-impermeable underlays of the present invention provided liquid water impermeability even under the highest blotting pressures used while providing an adequate MVTR of greater than 100 g/m²/day. Comparative examples failed the blotting test, or, in the case of impermeable thermoplastic films such as Comparative Example C, acted as an undesirable moisture vapor barrier.

10

15

20

25

30

35

WHAT IS CLAIMED IS:

1. A carpet underlay comprising a composite of a fibrous substrate having
5 opposite first and second planar sides, and at least one film affixed to the first side
of said substrate, said underlay impermeable to liquids and permeable to moisture
vapor.
2. The underlay of Claim 1 further comprising an optional control layer
10 affixed to said substrate, a tie layer affixed to said control layer or to said
substrate, and wherein said is film affixed to said tie layer, said underlay
impermeable to liquids and differentially permeable to moisture vapor.
3. The underlay of Claim 1 or 2 wherein the film has a first layer and
15 second layer, each of said layers being comprised of a different moisture vapor
permeable polymer composition wherein one layer is hydrophilic and one layer is
hydrophobic.
4. The underlay of Claim 1 or 2 wherein the fibrous substrate is a woven
20 or nonwoven fabric or web selected from the group consisting of polyester,
poly(trimethylene terephthalate), polyolefin, polyamide, synthetic fibers, natural
fibers, bicomponent fibers, cellulosic fibers, wool, cotton, acrylic, jute, and
copolymers and blends thereof.
- 25 5. The underlay of Claim 1 or 2 wherein the film is selected from the
group consisting of vulcanized silicone rubber, silicone polymer, polyurethane,
polyether ester, polyether amide, polyurethane ester, polyurethane ether, polyvinyl
alcohol, and copolymers and blends thereof.
- 30 6. The underlay of Claim 1 or 2 wherein the fibrous substrate is a
polyester spun-laced nonwoven fabric and the film is a butylene/poly(alkylene
ether) phthalate copolymer.
7. The underlay of Claim 1 or 2 wherein the underlay has a minimum
35 moisture vapor transmission rate of 100g/m² per day.

8. The underlay of Claim 2 wherein the control layer is a polymer capable of reducing the moisture vapor transmission rate of the composite, said control
5 layer selected from the group consisting of polyethylene, polypropylene or a copolymer or blend thereof, and wherein the tie layer is a copolymer of ethylene co-monomer units and vinyl acetate co-monomer units.

9. A tufted pile carpet comprising:
10 a) a primary backing having a surface tufted with pile yarns and an underside to which a latex has been applied;
b) an optional secondary backing having a surface and an underside, wherein the surface of the secondary backing is adhered to the underside of the primary backing; and
15 c) an underlay of Claim 1 or 2 adjacent to or affixed to the primary or secondary backing.

10. A carpet cushion of a material providing resiliency, support, or noise reduction having opposite first and second planar sides and having adjacent to or
20 affixed to said first side an underlay of Claim 1 or 2.

11. A process for rendering a carpet or a carpet cushion impermeable to liquids and permeable to moisture vapor comprising placing adjacent to or affixing to an underside of said carpet or said carpet cushion an underlay of Claim
25 1 or 2.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 00/28150

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 D06N7/00 A47G27/04 B32B27/12

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D06N A47G B32B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

| Category * | Citation of document, with indication, where appropriate, of the relevant passages | Relevant to claim No. |
|------------|--|-----------------------|
| A | WO 96 33307 A (DU PONT) 24 October 1996 (1996-10-24) claims 1,2,8,9 | 1,4,6, 9-11 |
| A | US 5 601 910 A (...) 11 February 1997 (1997-02-11) cited in the application | |
| A | WO 98 12375 A (DU PONT) 26 March 1998 (1998-03-26) claims 1,2 | 1,4,6, 9-11 |
| A | DE 197 12 671 A (HOELTER HEINZ) 1 October 1998 (1998-10-01) the whole document | 1,9 |

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- *S* document member of the same patent family

Date of the actual completion of the international search

8 February 2001

Date of mailing of the international search report

22/02/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5618 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Pamies Olle, S

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 00/28150

| Patent document cited in search report | Publication date | Patent family member(s) | Publication date |
|---|---------------------|--|--|
| WO 9633307 A | 24-10-1996 | US 5601910 A AU 710831 B AU 5548096 A CA 2218386 A EP 0821747 A JP 11514408 T US 5763040 A | 11-02-1997 30-09-1999 07-11-1996 24-10-1996 04-02-1998 07-12-1999 09-06-1998 |
| US 5601910 A | 11-02-1997 | AU 710831 B AU 5548096 A CA 2218386 A EP 0821747 A JP 11514408 T WO 9633307 A US 5763040 A | 30-09-1999 07-11-1996 24-10-1996 04-02-1998 07-12-1999 24-10-1996 09-06-1998 |
| WO 9812375 A | 26-03-1998 | AU 7075396 A EP 0927274 A | 14-04-1998 07-07-1999 |
| DE 19712671 A | 01-10-1998 | DE 29724305 U | 11-01-2001 |